

Product	Solid %	Viscosity	Solvent	OH %	Acid Value	Characteristics
Atrecryl A204/40 X MPA	40	3-10 dPas	X	-		Hard polymer for the production of colour stable varnishes with extremely fast drying properties, good durability and high hardness
Atrecryl A143/40 T	40	500-700 mPas	T			For high quality lacquers with good adhesion on metall and plastic, flexibility, lightfastness and weather resistance, compatible with most pigments, oil soluble colouring agents, zinc dust and aluminium bronze
Atrecryl H201/40 BA	40	4-9 Pas	BA	4,0		Hydroxy acrylate for universal PUR-Coatings and stoving enamels
Atrecryl A205/50 X	50	50-80 sec.	X	-	max. 2	Hard polymer for the production of very fast drying lacquers with durable surfaces
Atrecryl H201/50 X	50	5-10 dPas	X	4,0	max. 5	Hydroxy acrylate for universal PUR-Coatings and stoving enamels
Atrecryl H204/50 X MPA	50	45-70 dPas	X/MPA	1,8	max. 3	Hydroxy acrylate with high viscosity for fast curing, stackable wood and plastic PUR lacquers, extremely long pot life
Atrecryl H208/50 X	50	6-12 dPas	X	2,0		Hydroxy acrylate for PUR-coatings and stoving enamels, for wood, plastic and metall coatings, suitable for acrylic acid hardening lacquers
Atrecryl H239/50 X BA	50	60-90 dPas	X/BA	2,0	10-13	Fast drying hydroxy acrylate for wood, furniture and plastic lacquers with very good CAB, NC and Desmodur compatibility

Acrylic Resins



Product	Solid %	Viscosity	Solvent	OH %	Acid Value	Characteristics
Atrecryl H253/50 X MI	50	40-45 dPas	X/MI	1,8		Hydroxy acrylate for baking enamels and 2-K PUR lacquers with high reactivity, also for industrial wood coatings with good antiblocking
Atrecryl A196/50 IPA	50	80-180 dPas	IP			For print inks, for plastic and metall coatings, water dilutable
Atrecryl A229/50 X	50	7-9 dPas	X			Thermoplastic acrylic resin for 1-K car repair lacquers and aerosols, fast solvent release, high hardness, compatible with propellants propane/butane, resistant against overflowing fuel
Atrecryl A305/50 K3	50	30-50 dPas	WS	-	max. 2	IBMA acrylate, good solvent release, for fast drying lacquers with highly resisting and hard surfaces, improves drying properties of middle and long oil alkyd resins, lightfastness and resistance against yellowing and alkaline hydrolysis
Atrecryl A332/55 K3	55	10-15 dPas	WS	-	max. 3	Petrol soluble copolymerisate with physical drying properties for deep penetrating primers, impregnations and hydrophobing agents, good adhesion on glass and ceramic
Atrecryl A561/55 K3	55	8-12 dPas	WS	-		For deep penetrating primers, hydrophobing agents, wall paints, garage plaster, good pigment wetting, penetrating depth, good adhesion on zinc, glass and ceramik
Atrecryl H1538/55 SN BG	55	4900-7600 mPas	SN/BG	-	68 - 72	Cross linkable, carboxylated acrylic resin for can coating, high flexibility, chemicals resistance
Atrecryl H1539/55 SN BG	55	3800-5500 mPas	SN/BG	-	70 - 74	Cross-linkable, carboxylated acrylic resin for can coating, high flexibility, chemicals resistance
Atrecryl H249/55 SN BG	55	90-145 dPas	SN/BG			Cross-linkable carboxylated acrylate resin for can coating, high gloss, high hardness

Acrylic Resins



Product	Solid %	Viscosity	Solvent	OH %	Acid Value	Characteristics
Atrecryl A55/55 K3 SN	55	60-130 dPas	SN			Copolymer for deep penetrating and barrier primers, sealing compounds, house paints and plasters on porous substrates, excellent penetration depth, excellent consolidation of porous substrates, excellent resistance against alkaline hydrolysis and weathering
Atrecryl A2080/55 BA EA	55	9-16 dPas	BA/EA			Styrene acrylic copolymer, amongst others for traffic paints, good ageing resistance, lightfastness and weather resistance.
Atrecryl N2022/58 X BA	58	15-25 dPas	X/BA	1,4	max. 5	Polyacrylacrylate, containing OH groups, for PUR-coating and stoving enamels, fast drying, good adhesion on PP without pretreatment
Atrecryl A2080/60 BA	60	16-22 dPas	MEK / A		max. 15	Styrene acrylic copolymer, amongst others for traffic paints, good ageing resistance, lightfastness and weather resistance.
Atrecryl A332/60 D4 BA	60	25-38 dPas	AN/BA	-		Petrol soluble copolymerisate with physical drying properties for deep penetrating primers, impregnations and hydrophobing agents, good adhesion on glass and ceramic
Atrecryl H216/60 X BA	60	120-160 dPas	X/BA	2,5	max. 3	Hydroxy acrylate copolymer for PUR varnishes and primers, wood, plastic and metall model building, Florida test: good, ductile
Atrecryl H219/60 X	60	70-100sec.	X	2,7		In combination with aliphatic polyisocyanites suitable for the production of good adhering effect coatings with high mechanical resistance, high gloss, excellent durability, good adhesion
Atrecryl H232/60 XBS	60	100-130 sec.	XBS	3,6	max. 15	Special hydroxy acrylate resin for the production of industrial and car repair lacquers, fast surface and through drying, good flow, high gloss, weather resistant
Atrecryl H235/60 XBS	60	22-37 sec.	XBS		10-15	Special hydroxy acrylate resin for the production of industrial and car lacquers and clear coats, fast surface and through drying, good flow, high gloss, weather resistant

Acrylic Resins



Product	Solid %	Viscosity	Solvent	OH %	Acid Value	Characteristics
Atrecryl H245/60 X BA	60	80-140 sec.	X/BA	1,4		Polyacrylacrylate, containing OH groups, for PUR and stoving enamels in industrial applications, fast drying
Atrecryl H254/60 SI	60	20-30 dPas	S1	2,6	max.10	Hydroxy acrylate resin for fast drying PUR lacquers, good lightfastness and chalking resistance; application by brush or spray; qualified for heavy corrosion protection
Atrecryl H259/60 BA	60	80-120 dPas	BA	2,0		Acrylate resin with very good CAB, NC and Desmodur compatibility for wood, furniture and plastic lacquers, fast drying, low viscosity
Atrecryl H233/60 X Y	60	100-130 sec.	X Y	3,6		Hydroxy acrylate resin for the production of medium solid car repair lacquers, good flow, fast surface and through drying, high gloss, weather resistance
Atrecryl H245/60 SN	60	70-100 sec.	SN	1,4		Hydroxy acrylate resin for the production of PUR-coatings and baking enamels, fast drying, flexibility, good adhesion on non iron metals and plastics
Atrecryl H229HS/65 BA X	65	15-29 dPas	BA/X	4,5		Special modified hydroxy acrylate resin for high solid PUR lacquers, high film build, excelent gloss and flow
Atrecryl H264/65 MPA	65	30-50 dPas	MPA	2,6	max.10	Hydroxy acrylate resin for high solid 2-K PUR lacquers, excellent flow; good lightfastness and chalking resistance
Atrecryl H243HS/70 BA	70	35-45sec.	BA	3,3	max.15	Special hydroxy acrylate resin for high solid car repair and industrial lacquers, high body, high gloss, good flow, good drying properties
Atrecryl H255HS/70 BA	70	20-55 dPas	BA	3,1		Hydroxy acrylate resin for 2-K systems with higher solid content and good weather resistance

Acrylic Resins



Product	Solid %	Viscosity	Solvent	OH %	Acid Value	Characteristics
Atrecryl H255HS/70 EEP	70	40-60 dPas	EEP	3,1	max. 8	Hydroxy acrylate resin for 2-K systems with higher solid content and good weather resistance, good drying properties, high gloss
Atrecryl H270HS/70 BA	70	100-140 dPas	BA	3,1		Special hydroxy acrylate for high solid car repair and industrial lacquers, high body, high gloss, good flow, good adhesion on zinc
Atrecryl H248/70 BA EPA	70	26-32 sec.	BA/EPA	3,3		Special hydroxy acrylate resin with low viscosity and high filling power
Atrecryl H251/73 BA EPA	73	18-22 sec.	BA/EPA	3,1		Hydroxy acrylate resin for high solid 2-K PUR lacquers, excellent flow
Atrecryl H243HS/75 X BGA	75	35-45sec.	X/BGA	3,3		Special hydroxy acrylate resin for high solid car repair and industrial lacquers, high body, high gloss, good flow, good drying properties
Atrecryl H255HS/75 BA	75	25-55 dPas	BA	3,1		Hydroxy acrylate resin for 2-K systems with increased solid content and good weather resistance, good drying properties, high gloss
Atrecryl H255HS/75 EEP	75	40-60 dPas	EEP	3,1		Hydroxy acrylate resin for 2-K systems with increased solid content and good weather resistance, good drying properties, high gloss
Atrecryl H262HS/75 EMB	75	100-120sec.	EMB	3,3-3,5	5 - 10	Hydroxy acrylate resin for 2-K systems with increased solid content and excellent weather resistance, good adhesion, good Florida test
Atrecryl A467/75 EA BA	75	200-300 dPas	EA/BA			Polyacrylic copolymer for sealing compounds and putties, stable on storage, durable flexibility, cold crack and weather resistant

Product	Solid %	Viscosity	Solvent	OH %	Acid Value	Characteristics
Atrecryl H262HS/80 EMB	80	55-75 dPas	EMB	3,3		Hydroxy acrylate resin for 2-K systems with increased solid content and excellent weather resistance, good adhesion, good Florida test
Atrecryl H271CHS/80 EMB	80	35-55 dPas	EMB	2,8-3,0	max.13	Special modified hydroxy acrylate resin for 2-K systems with low viscosity, good weather resistance, good adhesion
Atrecryl B2987	100	500-1500 dPas	no	-		An ageing-resistant and lightfast acrylic copolymer suitable for plastification. As a non migrating plasticiser it is suitable for plastification of most acrylates
Atrecryl B2272	100	18-24 Pas	no	-		Solvent free acrylic copolymer, good adhesion on substrates like concrete, bricks, marble, glass, flagging, wood, to be used in sealing compounds and putties

Solvent

WS=White Spirit; AN=Aliphatic Naphtha; IPA=Isopropanol; BA=Butylacetat; X=Xylene; EMP=Ethoxy-, Methoxypropanol; MEK=Methylethylketon; A=Aceton; SN=Solvent Naphta 150; S1= Solvent Naphta 100; BG=Butylglycol;MPA=Methoxypropylacetat; MI=Methyl-Isobutylketon; BGA=Butylglykolacetat; EEP=Ethylethoxypropionat; XBS=conglomeration of Xylol, Butylacetat, Solvent Naphta; EMB: conglomeration of EEP, MPA und BA; TPnB=Dowanol TPnB; Y=further solvent additives; no=solventfree