

ATRESIN C 707

Saturated Carboxylated Polyester Resin with Medium Reactivity

Specification:

Property	Range	Method / According to standard
Acid value	68 - 74 mg KOH/g	AA HL 10 01-0
Tg	54 - 62 °C	AA HL 10 03-1
Viscosity, 150 °C	20 - 40 Pa·s	AA HL 10-07-1

Characteristics and Use:

- » In combination with epoxy resins for powder coatings with very good flow and excellent gloss.
- » Recommended ratio: polyester / epoxy ratio : 50 / 50.

Delivery form:

Granules with a maximum particle size of 12 mm.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between -20 °C and 30 °C, for up to 12 months. Protect from freezing and avoid exposure to direct sunlight.

Based on the experience the shelf life of the resin is minimal 5 years. It is recommended to check the acid value and the viscosity every year.

Starting Point Formulation

Component	Weight
Atresin C 707	30
Epoxy resin	30
Flow agent	1.0
Benzoin	0.4
Titan dioxide	35
Blanc Fixe	3.6

Manufacturing and application method:

- » Extruder: 2x Buss-Ko-Kneter.
- » Casing setting temperature: 110 °C.
- » ESB-spray gun, Corona, voltage: 80 kV.
- » 0,75 mm steel panel, pretreated with zinc phosphate, aprox. 60 - 70 µm coating thickness.
- » Stoving in an air circulated oven - Heraeus UT 6120.

Stoving cycles:

10 minutes at 180 °C (object temperature).

Film properties:

Property	Value	Method / According to standard
Gloss at 60°	max. 90	DIN EN ISO 2813
Cupping test (Erichsen)	≥ 8 mm	DIN 53156 / ISO 1520

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: April 2025

Page: 2/2