

Product code: 479359

DOMACRYL 5124 75 BAc

Hydroxy Acrylic Resin



Specification:

Property	Range	Method / According to standard
Non-volatile matter	74 - 76%	MH1155 / ISO 3251
Acid value on solid resin	5 - 10 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	120 - 145 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	3500 - 6500 mPa·s	MH1007 / ISO 3219
Colour	max. 100 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Density	1 kg/L
Flash point	25 °C
Hydroxyl content on solid	4.0%
Water content	max. 0.1 wt.%
Bio-based content on solid	7%
Total renewable content on delivery form	5%

Solubility:

Soluble in xylene, acetone, ethyl acetate, n-butyl acetate, methoxy propyl acetate and methyl isobutyl ketone.

Compatibility:

Compatible with isocyanate resins and majority of other Domacryl hydroxy resins.

Applications:

- » Highly reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins. It has a broad compatibility with similar acrylic resins.
- » Coatings based on Domacryl 5124 75 BAc have good balance between hardness and flexibility, with excellent mechanical properties and superior outdoor durability.
- » Used for room temperature drying or forced drying two-pack systems for automotive refinishing (clear and pigmented top coats), ACE and high quality industrial coatings.
- » Supply form in butyl acetate is suitable for aromatic-free systems and gives high solids system at spraying viscosity (VOC ≤ 420 g/l).
- » Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: March 2025

Page: 1/1