

Product code: 477706

DOMACRYL 5262 75 BA_c/EEP/MPA

Hydroxy Acrylic Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	74 - 76%	MH1155 / ISO 3251
Acid value on solid resin	5 - 12 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	90 - 120 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C, 50 s ⁻¹	13000 - 18000 mPa·s	MH1007 / ISO 3219
Colour	max. 50 APHA	MH1125 / ISO 6271

Typical properties:

Property	Value
Solvent ratio	Butyl acetate / Ethyl 3-ethoxypropionate / MPA = 2 / 1.5 / 1
Density	1 kg/L
Flash point	27 °C
Hydroxyl content on solid	3.3%
Water content	max. 0.1 wt.%

Solubility:

- » Soluble in xylene, toluene, acetone, ethyl acetate, n-butyl acetate, methoxy propyl acetate, methyl isobutyl ketone.
- » Limited solubility in aromatic solvent 100 and aromatic solvent 150.

Compatibility:

Compatible with isocyanate resins: HDI-isocyanurate, HDI-biuret and other binders: Vinyl VAGH, nitrocellulose (ester soluble), majority of other Domacryl hydroxy resins.

Applications:

- » Highly reactive hydroxy acrylic resin intended for crosslinking with isocyanate resins with a fast build-up of hardness.
- » Used for very fast air or forced drying of two-pack systems for automotive refinishing (top and clear coats) with excellent mechanical properties and superior outdoor durability.
- » Crosslinking with aliphatic isocyanates is recommended for the formulation of non-yellowing finishing. Physical drying can be accelerated with the addition of CAB resins.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: March 2025

Page: 1/1