

Product code: 479342

DOMACRYL 920

Methacrylate Resin

Specification:

Property	Range	Method / According to standard
Viscosity, 23 °C	100 - 130 mPa·s	MH1007 / ISO 3219

Typical properties:

Property	Value
Appearance	Bluish opaque liquid
Refractive index	1.44

Remarks:

- » Low viscosity, fast curing methacrylate resin, used for permanent cold spray plastic road markings.
- » Markings based on Domacryl 920 are permanently elastic, weather resistant and resistant to abrasion, road salts and fuels.
- » Domacryl 920 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- » Domacryl 920 is amine pre-activated.

Applications:

- » Binder for cold spray plastic road markings, hardened with dibenzoyl peroxide.
- » Particularly suitable for spray application (drop-on-procedure) with reactive glass beads in the 100:2 systems with special spray machines and 1:1 system with Domacryl 922 which is not pre-accelerated.
- » Recommended layer thickness is 0.4 - 0.8 mm.
- » Recommended application temperature is between 5 and 40 °C.
- » Domacryl 920 has a mild odour.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: February 2025

Page: 1/1