Product code: 402664

DOMACRYL 936

Methacrylate Resin

Specification:

Property	Range	Method / According to standard
Viscosity, 23 ºC	90 - 100 mPa·s	MH1007 / ISO 3219
Colour	max. 1 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Appearance	Opaque liquid
Refractive index	1.44
Recycled content	30%

Remarks:

- Markings based on Domacryl 936 are permanently elastic, weather resistant and resistant to abrasion, road salts and fuels.
- Domacryl 936 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- Domacryl 936 is amine pre-activated.
- The resin contains 30% recycled chemical content derived from recycled feedstocks.

Applications:

- Binder for two component road markings, hardened with dibenzoyl peroxide.
- Used for marking of pedestrian crossings, stop lines, direction arrows and safety markings with increased night visibility.
- Particularly suitable for manual application with smoothing trowels or draw box machines to asphalt and concrete roads.
- Domacryl 936 can be used alone or in combination with Domacryl 939 for three component systems.
- Recommend layer thickness is 1 - 2 mm.
- Recommended application temperature is between 10 and 45 °C.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

Disclaimer
This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

Copyright © Helios Resins & Atcoat | **www.resinshelios.com** | **www.atcoat.com**