

Product code: 900488

DOMACRYL 948

Methacrylate Resin

Specification:

Property	Range	Method / According to standard
Viscosity, 23 °C	300 - 350 mPa·s	MH1007 / ISO 3219
Colour	max. 1 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Appearance	Opaque liquid
Refractive index	1.44

Remarks:

- » Markings based on Domacryl 948 are permanently elastic, weather resistant and resistant to abrasion, road salts and fuels.
- » Domacryl 948 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- » Domacryl 948 is amine pre-activated.

Applications:

- » Binder for thin two component markings, hardened with dibenzoyl peroxide.
- » Mainly used for large area markings such as bike paths, bus lines, restricted parking areas and other coloured traffic zones.
- » Particularly suitable for manual application by roller or smoothing trowels.
- » Recommended layer thickness is 1 - 2 mm.
- » Recommended application temperature is between 10 and 40 °C.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: February 2025

Page: 1/1