

Product code: 407908

DOMALKYD 4333 70 BAc

Alkyd Resin Modified with Soybean Fatty Acids

Specification:

| Property | Range | Method / According to standard |
|-------------------------------|-------------------|--------------------------------|
| Non-volatile matter | 69 - 71% | MH1155 / ISO 3251 |
| Acid value on solid resin | 25 - 35 mg KOH/g | MH1051 / ISO 2114 |
| Hydroxyl value on solid resin | 70 - 110 mg KOH/g | MH1052 / ISO 4629 |
| Viscosity, 23 °C | 1400 - 2000 mPa·s | MH1007 / ISO 3219 |
| Colour | max. 6 Gardner | MH1124 / ISO 4630 |

Typical properties:

| Property | Value |
|-------------|-------|
| Oil content | 33% |

Solubility:

Soluble in aromatic hydrocarbons, esters, ketones and higher alcohols.

Compatibility:

- Compatible with short oil alkyd resins, nitrocellulose, colophonium modified maleic resins, urea and melamine resins, castor oil and polyisocyanate resins.
- Incompatible with long and medium air-drying alkyds and drying oils.

Applications:

- > Used in lacquers and enamels for wood in combination with nitrocellulose and polyisocyanate
- >> resins.
- It gives 2K PUR combination lacquers with good levelling and fast drying properties.
- >> Due to its excellent wetting properties, it is highly recommended for pigment pastes.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: March 2025

Page: 1/1