

Product code: Provisional

DOMEMUL AA 7765

Self-crosslinking Acrylic Emulsion

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	44 - 46%	MH1155 / ISO 3251
Viscosity, 23 °C	20 - 350 mPa·s	MH1007 / ISO 3219
pH	7 - 8	MH1040 / ISO 976

Typical properties:

Property	Value
Solvent	Water
Appearance	Slightly brownish
Density	1.06 kg/L
MFFT	31°C
Bio-based and recycled content on solid	38%
Total renewable content on delivery form	72%

Remarks:

The bio-based content is 15% of the dry matter by the Carbon-14 method.

Applications:

- » Domemul AA 7765 is a surfactant-low acrylic emulsion for industrial waterborne wood finishes, interior.
- » Good chemical and mechanical resistance, wetting, low-foaming, flow and transparency.
- » Hand cream resistance, fast drying and hardness.
- » For better film formation, the use of a coalescent is advised.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 6 months. Protect from freezing and avoid exposure to direct sunlight.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: February 2025

Page: 1/1