

Product code: 472090

DOMEMUL SA 9262 APEO-free

APEO-free Styrene-acrylic Emulsion

Specification:

Property	Range	Method / According to standard
Non-volatile matter	41 - 43%	MH1155 / ISO 3251
Viscosity, 23 °C	50 - 250 mPa·s	MH1007 / ISO 3219
pH	8.0 - 8.5	MH1040 / ISO 976

Typical properties:

Property	Value
Solvent	Water
Appearance	Milky white
Density	1.0 kg/L
MFFT	30 °C

Remarks:

Domemul SA 9262 APEO-free, can be combined with urethanes and alkyds.

Applications:

- » Designed for industrial waterborne coatings: anticorrosive primers, metal finishes, plastic and wood.
- » Recommended for application with good adhesion to metal and good humidity resistance.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 35 °C, for up to 12 months. Protect from freezing and avoid direct sunlight.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: February 2025

Page: 1/1