Product code: Provisional

DOMOPOL 5106 60 SAB/BG ND

Saturated Polyester Resin

Specification:

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	3 - 6 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	28 - 35 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 ºC	4000 - 5000 mPa·s	MH1007 / ISO 3219
Colour	max. 3 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Solvent ratio	Aromatic solvent 150 ND / Butylglycol = 1 / 1
Density	1.1 kg/L
Molecular weight	4500
Flash point	63 °C
Hydroxyl content on solid	1%
Tg	26 °C
Maximum ISSC PLUS-certified content allocated using the mass balance approach, on a dry solids basis	11%

Remarks:
The share of ISCC PLUS certified material is determined individually for each delivery based on the applicable mass balance allocation and is specified in the corresponding Sustainability Declaration. The validity of the ISCC PLUS certificate can be verified via the official website (https://iscc-system.org/).

Solubility:
Soluble in aromatic hydrocarbons, esters and glycol ethers.

Compatibility:
Compatible with amino resins and blocked polyisocyanate resins.

Applications:
Domopol 5106 60 SAB/BG ND is intended for coil coatings: domestic appliances and outdoor durable systems with high flexibility and stain resistance.

Storage:
The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided. Domopol 5106 may, due to low temperatures or long storage, become turbid. Heating to around 60 °C or adding solvent will re-homogenise the product.

Disclaimer
This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.