

Product code: 419930

## DOMOPOL 5117 60 SAB ND

### Saturated Polyester Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	5 - 10 mg KOH/g	MH1051 / ISO 2114
Hydroxyl value on solid resin	22 - 30 mg KOH/g	MH1052 / ISO 4629
Viscosity, 23 °C	14000 - 18000 mPa·s	MH1007 / ISO 3219
Colour	max. 2 Gardner	MH1124 / ISO 4630

**Typical properties:**

Property	Value
Density	1.1 kg/L
Molecular weight	5500
Flash point	63 °C
Hydroxyl content on solid	0.8%
Tg	25 °C
Bio-based content on solid	23%
Total renewable content on delivery form	14%

**Remarks:**

The bio-based content is 23% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

**Solubility:**

Soluble in aromatic hydrocarbons, esters and glycol ethers.

**Compatibility:**

Compatible with amino resins and blocked polyisocyanate resins.

**Applications:**

- » Domopol 5117 60 SAB ND is intended for can coatings – white base coats, tube coating.
- » Principal properties are deep drawn flexibility and cold crush flexibility.

**Storage:**

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided

**Disclaimer**

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at [www.helios.si](http://www.helios.si). Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

**TECHNICAL DATASHEET**

Copyright © Helios Resins & Atcoat | [www.resinshelios.com](http://www.resinshelios.com) | [www.atcoat.com](http://www.atcoat.com)

Issue Date: March 2025

Page: 1/1