

Product code: 479346

DOMOPOL 5172 55 SAB/MPA ND

Saturated Polyester Resin



Specification:

Property	Range	Method / According to standard
Non-volatile matter	54 - 56%	MH1155 / ISO 3251
Acid value on solid resin	0 - 3 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	2000 - 4000 mPa·s	MH1007 / ISO 3219
Colour	max. 3 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Solvent ratio	Aromatic solvent 150 ND / Methoxy propyl acetate = 4 / 1
Density	1.1 kg/L
Molecular weight	6000
Flash point	45 °C
Hydroxyl content on solid	0.9%
Tg	30 °C
Bio-based content on solid	25%
Total renewable content on delivery form	14%

Remarks:

The bio-based content is 25% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Applications:

- » Domopol 5172 55 SAB/MPA ND is recommended for can coatings such as metal decorating enamels.
- » In coil coatings, it can be used for topcoats in interior architecture.
- » This product may be suitable for other coil coating applications, such as appliance finishing, primers for hot dip galvanized steel, and primers for aluminium.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: March 2025

Page: 1/1