

Product code: 479343

DOMOPOL 5176 60 SA

Saturated Polyester Resin

**Specification:**

Property	Range	Method / According to standard
Non-volatile matter	59 - 61%	MH1155 / ISO 3251
Acid value on solid resin	max. 10 mg KOH/g	MH1051 / ISO 2114
Viscosity, 23 °C	3500 - 5500 mPa·s	MH1007 / ISO 3219
Colour	max. 4 Gardner	MH1124 / ISO 4630

Typical properties:

Property	Value
Flash point	41 °C
Hydroxyl content on solid	3%
Bio-based content on solid	36%
Total renewable content on delivery form	22%

Remarks:

The bio-based content is 36% of the dry matter via a biomass balance (BMB) approach as certified by the ISCC PLUS. The certificate can be issued upon request.

Applications:

- » Domopol 5176 60 SA is intended for can coating overprint varnish (wet-on-wet), general industry finishes and automotive top coats (OEM).
- » The resin has high gloss level, outdoor durability, very good pigment wetting and good yellowing resistance.

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures below 35 °C, for up to 12 months. Exposure to direct sunlight should be avoided.

Disclaimer

This data is based on experience, for its completeness, we assume no liability. As we take no influence on the processing, it lies within the obligation of the customer to test, whether it is suitable for the intended purpose, before using the product. Any change in the processing procedure, the environmental conditions or the failure to comply with instructions may unfavorably influence the result. This Technical Datasheet is available on our website at www.helios.si. Should there be any discrepancies between this document and the version that appears on the website, then the version on the Website will take precedence.

TECHNICAL DATASHEET

Copyright © Helios Resins & Atcoat | www.resinshelios.com | www.atcoat.com

Issue Date: March 2025

Page: 1/1